



FOAMGLAS® T3+

Page: 1

Date: 01.08.2021

Supersedes: 01.03.2020

www.foamglas.com



FOAMGLAS® T3+ is available in two sizes.

Form of delivery (content per package)

length x width [mm]	600 x 450							
thickness [mm]	50	60	70	80	90	100	110	120
R _D [m²K/W]	1.35	1.65	1.90	2.20	2.50	2.75	3.05	3.30
Units per package	10	8	7	6	6	5	5	4
square metre [m²]	2.70	2.16	1.89	1.62	1.62	1.35	1.35	1.08

length x width [mm]	600 x 450							
thickness [mm]	130	140	150	160	170	180	190	200
R _D [m²K/W]	3.60	3.85	4.15	4.40	4.7	5.0	5.25	5.55
Units per package	4	4	3	3	3	3	3	3
square metre [m²]	1.08	1.08	0.81	0.81	0.81	0.81	0.81	0.81

length x width [mm]	1200 x 600							
thickness [mm]	80	100	120	140	150	160	180	
R _D [m²K/W]	2.20	2.75	3.30	3.85	4.15	4.40	5.0	
Units per pallet*	24	18	16	14	12	12	10	
square metre [m²]	17.28	12.96	11.52	10.08	8.64	8.64	7.20	

Other dimensions and thicknesses are available on request.

* No single package, but all slabs on a pallet.

General FOAMGLAS® Cellular Glass Insulation characteristics

- Description : FOAMGLAS® insulation is manufactured from specially graded recycled glass** and natural raw materials which are available in abundant supply (sand, dolomite, lime...). The insulation is totally inorganic, contains no ozone depleting propellants, flame resistant additives or binders. Without VOC or other volatile substances.
- Reaction to fire (EN 13501-1) : Core material complying with Euroclass A1, non-combustible, no toxic fumes
- Service temperature limits : from -265°C to +430°C
- Water vapour resistance (EN ISO 10456) : $\mu = \infty$
- Hygroscopicity : zero
- Capillarity : zero
- Melting point (cf DIN 4102-17) : >1000 °C
- Thermal expansion coefficient (EN 13471) : $9 \times 10^{-6} \text{ K}^{-1}$
- Specific heat (EN ISO 10456) : 1000 J/(kg·K)

FOAMGLAS® characteristics

Time-tested thermal performance	Waterproof	Resistant to attack	High compressive strength	Acid resistant / chemical resistant
Non-combustible	Impervious to water vapour	Dimensionally stable	Ecological	Radon protection stable



FOAMGLAS® T3+

Page: 2 Date: 01.08.2021 Supersedes: 01.03.2020 www.foamglas.com

1. Product characteristics according to EN 13167 ¹⁾

Density (± 15%) (EN 1602)	: 100 kg/m ³
Thickness (EN 823) ± 2 mm	: from 50 to 200 mm (see table page 1)
Length (EN 822) ± 5 mm	: 600 mm
Width (EN 822) ± 2 mm	: 450 mm or 1200 mm
Thermal conductivity (EN ISO 10456)	: $\lambda_D \leq 0.036$ W/(m·K)
Reaction to fire (EN 13501-1)	: Euroclass A1
Point load (EN 12430)	: PL ≤ 1.5 mm
Compressive strength (EN 826 annexe A)	: CS ≥ 500 kPa
Bending strength (EN 12089)	: BS ≥ 400 kPa
Tensile strength (EN 1607)	: TR ≥ 150 kPa
Compressive creep (EN 1606)	: CC (1.5/1/50) 225

¹⁾ CE-marking ensures conformity with the mandatory essential requirements of CPD as mentioned in EN 13167; within the CEN Keymark certification all mentioned characteristics are certified by an empowered, notified and accredited 3rd party.

2. Additional product characteristics

Environmental Product Declaration (ISO 14025 and EN 15804) : EPD-PCE-20150042-IBA1-DE

3. Application area

Insulation of:

- façades
- cavity walls
- belowgrade: walls
- walls and soffits; interior insulation behind brick lining, plasterboard stud wall construction

** recycled glass consists of highly selected postconsumer glass and highly selected production scrap/co-products.